

## Non-slip Heat Shrinking sleeve



Material: Polyolefin  
 Shrinking ratio: 2:1 (1.8:1)  
 Longitudinal shrink ratio:  $\leq \pm 8\%$   
 Tensile strength:  $\geq 8\text{MPa}$   
 Withstand voltage:  $\geq 1\text{kV/mm}$   
 Flammability: VW-1  
 Operating Temperature:  $-55 \sim 105^\circ\text{C}$   
 Minimum shrink temperature:  $70^\circ\text{C}$   
 Full recovery temperature:  $110^\circ\text{C}$



Type	Nominal size (mm)	Before shrink(ømm)		After shrink(ømm)		Contents
		Inner dia.	W.T	I.D. (max.)	W.T (min.)	
19008CA063	ø15	15±0.5	0.45±0.15	8.0	0.80	1.6 meter
19008CA064	ø18	18±0.5	0.45±0.15	9.5	0.80	1.6 meter
19008CA065	ø20	20±0.5	0.45±0.15	11.0	0.90	1.6 meter
19008CA066	ø22	22±0.6	0.5±0.15	12.5	0.90	1.6 meter
19008CA067	ø25	25±0.6	0.5±0.15	14.5	1.00	1.6 meter
19008CA068	ø28	28±0.6	0.55±0.2	15.5	1.00	1.6 meter
19008CA069	ø30	30±0.6	0.60±0.2	17.5	1.05	1.6 meter
19008CA070	ø35	35±0.6	0.65±0.2	20.0	1.10	1.6 meter
19008CA071	ø40	40±0.6	0.65±0.2	23.0	1.20	1.6 meter
19008CA072	ø45	45±0.6	0.70±0.2	25.0	1.25	1.6 meter
19008CA073	ø50	50±0.7	0.70±0.2	27.5	1.30	1.6 meter